

222 Cavalcade Street, 77009-3213
P.O. Box 8768, Houston, Texas 77249-8768
Tel: (713) 692-9151 Fax: (713) 696-6205

Attention: Bill Reinhardt
Rumber Materials, Inc.
621 West Division Street
Muenster, TX 76252
P: 940-759-4181 / F: 512/375-1972

W/O. No.: RUM004-06-28-88928-1
P.O. No.:
Report Date: 7/13/2005

Identification: Rumber Boards 6040


MATERIAL PROPERTY TESTING

TEST	METHOD	RESULT
Flash Ignition Temperature	ASTM D1929	620°F (327°C)
Self Ignition Temperature	ASTM D1929	820°F (438°C)
Flame Spread	ASTM D635	7 minutes, 30 seconds average over a 3" length, consumed 100%
Abrasion Resistance	ASTM D1037 ASTM F510	0.028% mass loss in 1,000 cycles 22.72 mm ³ volume loss in 1,000 cycles
Water Absorption	ASTM D1037	No water absorption
Water Absorption	ASTM D570	0.43%
Density	ASTM D792	0.924 g/cc
Specific Gravity	ASTM D792	0.982
Coefficient of Friction	ASTM C1028 ASTM D2394	Static coefficient of friction: Dry = 0.49. Wet = 0.46 Sliding coefficient of friction: Dry = 0.56 Wet = 0.54
Compressive Strength Modulus	ASTM D143	37,225 psi
Modulus of Elasticity	ASTM D4761	21,405 psi in center point loading of typical board 15,290 psi in center point loading for tongue/groove board
Modulus of Elasticity (Flexural Modulus)	ASTM D198	29,815 psi in two point loading of typical board 23,960 psi in two point loading of tongue/groove board
Coefficient of Linear Thermal Expansion	ASTM D696	6.1 x 10 ⁻⁵ (in/in. °C)

Our letters and reports are for the exclusive use of the client to whom they are addressed and shall not be reproduced except in full without the approval of the testing laboratory. The use of our name must receive our written approval. Our letters and reports apply only to the sample tested and/or inspected, and are not indicative of the quantities of apparently identical or similar products. Material submitted to our metals department will be discarded after a period of 30 days unless otherwise directed.

Stork SWL, is an operating unit of Stork Materials Technology B.V., Amsterdam, The Netherlands, which is a member of the Stork group

Respectfully Submitted


Terry Wilt
Manager, Product Evaluation